

Technical data sheet

Date: January 2023

QuickFill® White SE (F)

WHITE SACK KRAFT PAPER

Production Unit: Karlsborg

End uses

QuickFill® White SE (F) is particularly suitable for applications involving fast filling of valve sacks, where friction, printability and appearance are also important. High porosity means that the sacks do not normally need to be perforated. QuickFill® White SE (F) is approved in accordance with the German norm for dangerous goods.

Grammages

 $70 - 90 \text{ g/m}^2$

Materials

QuickFill® White SE (F) is produced from pure, white kraft pulp and consists entirely of virgin fibre. The long and strong fibres, from the slow-growing forests of the Nordic region, give the paper its inherent strength.

Approvals

QuickFill® White SE (F) is produced in compliance with BfR and FDA for food contact.

Certification

Karlsborg mill is certified in accordance with ISO 9001, ISO 14001, ISO 50001, FSC® CoC (FSC-C020000) and PEFC $^{\rm TM}$ CoC (PEFC/05-33-136).

Other information

(F) means that the product is produced with an embossed pattern.

| Property | Unit Typical valu | | | es es | | Method |
|-----------------------------|-------------------|----------|--------------|--------------|--------------|------------|
| Grammage | g/m² | | 70 | 80 | 90 | ISO 536 |
| Tensile strength | kN/m kN/m | MD CD | 4.9 3.5 | 5.6 4.0 | 6.3 4.5 | ISO 1924-3 |
| Tensile index | Nm/g Nm/g | MD CD | 70 50 | 70 50 | 70 50 | ISO 1924-3 |
| Stretch | % % | MD CD | 6.0 9.5 | 6.0 9.0 | 6.0 9.0 | ISO 1924-3 |
| TEA | J/m² J/m² | MD CD | 180 225 | 210 250 | 235 270 | ISO 1924-3 |
| TEA Index | J/g J/g | MD CD | 2.6 3.2 | 2.6 3.1 | 2.6 3.0 | ISO 1924-3 |
| TEA index geometric | J/g | | 2.9 | 2.8 | 2.8 | |
| Tear strength | mN mN | MD CD | 980 1050 | 1200 1280 | 1440 1485 | ISO 1974 |
| Tear index | mNm²/g mNm²/g | MD CD | 14.0 15.0 | 15.0 16.0 | 16.0 16.5 | ISO 1974 |
| Brightness | % | | 85 | 85 | 85 | ISO 2470 |
| Cobb 60s | g/m² | WS | 30 | 30 | 30 | ISO 535 |
| Air resistance | S | | 5 | 5 | 6 | ISO 5636-5 |
| Static friction coefficient | | | 0.7 | 0.7 | 0.7 | TAPPI T815 |
| Moisture | % | | 7.5 | 7.5 | 7.5 | ISO 287 |

MD = Machine Direction CD = Cross Direction

TS = Top side

WS = Wire side (winded outside, recommended print side)

Test climate: 50% RH, 23°C