

Technical data sheet

Date: January 2023

# QuickFill® White SE

WHITE SACK KRAFT PAPER

Production Unit: Karlsborg

#### End uses

QuickFill® White SE is particularly suitable for applications involving fast filling of valve sacks with powdered goods where printability and appearance are also important. High porosity means that the sacks do not normally need to be perforated. QuickFill® White SE is approved in accordance with the German norm for dangerous goods.

## **Grammages**

70 - 100 g/m<sup>2</sup>

### **Materials**

QuickFill® White SE is produced from pure, white kraft pulp and consists entirely of virgin fibre. The long and strong fibres, from the slow-growing forests of the Nordic region, give the paper its inherent strength.

### **Approvals**

QuickFill® White SE is produced in compliance with BfR and FDA for food contact.

#### Certification

Karlsborg mill is certified in accordance with ISO 9001, ISO 14001, ISO 50001, FSC® CoC (FSC-C020000) and PEFC™ CoC (PEFC/05-33-136).

Property	Unit		Typical values	;			Method
Grammage	g/m²		70	80	90	100	ISO 536
Tensile strength	kN/m kN/m	MD CD	4.9 3.5	5.6 4.0	6.3 4.5	7.0 5.0	ISO 1924-3
Tensile index	Nm/g Nm/g	MD CD	70 50	70 50	70 50	70 50	ISO 1924-3
Stretch	% %	MD CD	6.0 9.5	6.0 9.5	6.0 9.0	6.0 9.0	ISO 1924-3
TEA	J/m² J/m²	MD CD	180 225	210 250	235 270	260 300	ISO 1924-3
TEA Index	J/g J/g	MD CD	2.6 3.2	2.6 3.1	2.6 3.0	2.6 3.0	ISO 1924-3
TEA index geometric	J/g		2.9	2.8	2.8	2.8	
Tear strength	mN mN	MD CD	980 1050	1200 1280	1395 1485	1600 1700	ISO 1974
Tear index	mNm²/g mNm²/g	MD CD	14.0 15.0	15.0 16.0	15.5 16.5	16.0 17.0	ISO 1974
Brightness	%		85	85	85	85	ISO 2470
Cobb 60s	g/m²	TS	30	30	30	30	ISO 535
Air resistance	S		5	5	6	6	ISO 5636-5
Moisture	%		7.5	7.5	7.5	7.5	ISO 287

MD = Machine Direction CD = Cross Direction TS = Top side (winded outside, recommended print side)

WS = Wire side

Test climate: 50% RH, 23C