# BILLERUDKORSNÄS

Technical data sheet

Date: January 01 2018

## Performance White E WHITE SACK KRAFT PAPER

Production Unit: Pietarsaari

### End uses

Performance White E is an extensible sack paper recommended for sack applications where strength requirements are very high.

#### Grammages

70 – 90 g/m<sup>2</sup>

#### Materials

Performance White E is produced from pure, white kraft pulp and consists entirely of virgin fibre. The long and strong fibres, from the slow-growing forests of the Nordic region, give the paper its inherent strength.

#### Approvals

Performance White E is produced in compliance with BfR and FDA for food contact.

#### Certification

Pietarsaari mill is certified in accordance with ISO 9001, ISO 14001, OHSAS 18001 and FSSC 22000. Performance White E is available as FSC<sup>®</sup> certified paper (FSC-C113010) or PEFC<sup>™</sup> (PEFC/02-31-216) certified material.

| Property            | Unit             |          | Typical values |              |              | Method     |
|---------------------|------------------|----------|----------------|--------------|--------------|------------|
| Grammage            | g/m²             |          | 70             | 80           | 90           | ISO 536    |
| Tensile strength    | kN/m<br>kN/m     | MD<br>CD | 5.6<br>4.2     | 6.4<br>4.8   | 7.2<br>5.4   | ISO 1924-3 |
| Tensile index       | Nm/g<br>Nm/g     | MD<br>CD | 80<br>60       | 80<br>60     | 80<br>60     | ISO 1924-3 |
| Stretch             | %<br>%           | MD<br>CD | 7.5<br>8.5     | 7.5<br>8.5   | 7.5<br>8.5   | ISO 1924-3 |
| TEA                 | J/m²<br>J/m²     | MD<br>CD | 210<br>230     | 240<br>260   | 270<br>270   | ISO 1924-3 |
| TEA Index           | J/g<br>J/g       | MD<br>CD | 3.0<br>3.3     | 3.0<br>3.2   | 3.0<br>3.0   | ISO 1924-3 |
| TEA index geometric | J/g              |          | 3.1            | 3.1          | 3.0          |            |
| Tear strength       | mN<br>mN         | MD<br>CD | 910<br>1050    | 1120<br>1200 | 1260<br>1440 | ISO 1974   |
| Tear index          | mNm²/g<br>mNm²/g | MD<br>CD | 13<br>15       | 14<br>15     | 14<br>16     | ISO 1974   |
| Brightness          | %                |          | 84             | 84           | 84           | ISO 2470   |
| Cobb 60s            | g/m²             | WS       | 30             | 30           | 30           | ISO 535    |
| Air resistance      | S                |          | 18             | 18           | 18           | ISO 5636-5 |
| Moisture            | %                |          | 7.5            | 7.5          | 7.5          | ISO 287    |

MD = Machine Direction CD = Cross Direction TS = Top side (winded outside, recommended print side) Test of WS = Wire side

Test climate: 50% RH, 23C