

QuickFill® Brown SE BROWN SACK KRAFT PAPER

Production Unit: Skärblacka

End uses

QuickFill® Brown SE is particularly suitable for end-uses involving fast filling of valve sacks with powdered goods. High porosity means that the sacks do not normally need to be perforated. QuickFill® Brown SE is approved for sacks in accordance with the German norm for dangerous goods.

Grammages

70 – 90 g/m²

Materials

QuickFill® Brown SE is produced from pure, unbleached kraft pulp and consists entirely of virgin fibre. The long and strong fibres, from the slow-growing forests of the Nordic region, give the paper its inherent strength.

Approvals

QuickFill® Brown SE is produced in compliance with BfR and FDA food packaging norms

Certification

Skärblacka mill is certified in accordance with ISO 9001, ISO 14001 and ISO 50001.

Property	Unit		Typical values				Method
Grammage	g/m ²		70	80	85	90	ISO 536
Tensile strength	kN/m	MD	5.6	6.4	6.8	7.2	ISO 1924-3
	kN/m	CD	4.9	5.6	6.0	6.3	
Tensile index	Nm/g	MD	80	80	80	80	ISO 1924-3
	Nm/g	CD	70	70	70	70	
Stretch	%	MD	6.0	6.0	6.0	6.0	ISO 1924-3
	%	CD	8.0	7.5	7.5	7.0	
TEA	J/m ²	MD	215	250	265	270	ISO 1924-3
	J/m ²	CD	240	270	270	280	
TEA Index	J/g	MD	3.1	3.1	3.1	3.0	ISO 1924-3
	J/g	CD	3.4	3.4	3.2	3.1	
TEA index geometric	J/g		3.3	3.3	3.2	3.1	
Tear strength	mN	MD	910	1120	1190	1260	ISO 1974
	mN	CD	910	1120	1190	1260	
Tear index	mNm ² /g	MD	13.0	14.0	14.0	14.0	ISO 1974
	mNm ² /g	CD	13.0	14.0	14.0	14.0	
Friction coeff. Static		WS	0.60	0.60	0.60	0.60	ISO 15359
Cobb 60s	g/m ²		30	30	30	30	ISO 535
Air resistance	s		5	5	5	5	ISO 5636-5
Moisture	%		7.0	7.0	7.0	7.0	ISO 287

MD = Machine Direction
CD = Cross Direction

TS = Top side (winded outside, recommended print side)
WS = Wire side

Test climate: 50% RH, 23°C